

Faraz Oil Cut back Bitumen Grades Slow Curing (SC)

Characteristics	Unit	Specification								Test Method
		SC70		SC250		SC800		SC3000		
		Min	Max	Min	Max	Min	Max	Min	Max	
Kinematic Viscosity @ 60 °C	CST	70	140	250	500	800	1600	3000	6000	ASTM D-2170
Flash Point,	°C	66	-	79	-	93	-	107	-	ASTM D-92
Penetration @ 25 °C, 100 gm, 5 Second	CM	40	-	60	-	70	-	80	-	ASTM D-5
Distillate, volume percent of total distillate to 360 °C	°C	10	30	4	20	2	12	-	5	ASTM D-402
Ductility @ 25°C, Min	CM	100	-	100	-	100	-	100	-	ASTM D-113
Solubility in Trichloroethylene, Min	%	99.0	-	99.0	-	99.0	-	99.0	-	ASTM D-2042
Water. Max	%VOL	-	0.5	-	0.5	-	0.5	-	0.5	ASTM D-95