

Faraz Oil Oxidized bitumen

Characteristics	Unit	Specification				Test Method
		85/25	95/25	90/15	115/15	
Penetration @ 25 °C, 100 gm,5 Seconds	0.1 mm	20/30	20/30	10/20	10/20	ASTM D-5
Specific gravity @25 °C	gr/cm ³	1.01-1.05	1.01-1.05	1.01-1.05	1.01-1.05	ASTM D-70
Softening Point (R & B)	°C	80/90	90/100	85/95	110/120	ASTM D-36
Ductility @ 25 °C after TFOT, Min	Cm	1.5	1.5	3 Min	1.5	ASTM D-113
Loss on heating, Max	% wt	0.2	0.2	0.2 Max	0.2	ASTM D-6
Flash Point Cleveland open Cup, Min	°C	260	260	225	260	ASTM D-92